

TECHNICAL DATA SHEET

MALIEC RESIN

Product Code	Acid Value Mg KOH/gm	Viscosity 50% @ 30 ° c in FCBS	Melting Point ° c	Tolerance of 50 % solution	Color of 50 % solution in Solvent	Recommended Applications
601	135 – 140	16 – 20 in IMS	100 – 110	1 : α IMS	12 Max	Ball point inks, French Polish, liquid Inks and Picture Varnish.
602	132 – 135	25 – 35 in IMS	130 – 140	1 : α IMS	12 Max	Ball point inks, French polish, Liquid Inks, Paper Coatings and Picture Varnish.
603	25	25 – 35 in Toluene	125 – 135	1 : 10 MTO	12 Max	Synthetic Enamels, Air Drying hammer tone Paints, Letter press and Offset gloss Inks.
604	30 – 35	15 – 20 in Toluene	115 – 125	1 : 10 MTO	12 Max	NC Putty and Lacquer and Flexo Inks.