

TECHNICAL DATA SHEET

PENTA ESTER GUM

Product Code	Acid Value Mg KOH/gm	Viscosity 50% @ 30 ° c in FCBS\$	Melting Point ° c	Tolerance of 50 % solution	Color of 50 % solution in Solvent	Recommended Applications
701 Penta Estergum	20 Max	15 – 20 in Toluene	85 – 95	1 : α to MTO	10 Max	Primers, Aluminium paints, NC Lacquers, Adhesives.
702 Glycerol Estergum	20 Max	15 – 18 in Toluene	85 – 95	1 : α to MTO	10 Max	Adhesive, etc.
703 Calcium Resinate	75 – 80	50 – 70 in MTO	95 – 105	1 : α to MTO	10 Max	Primers and Foundry industries
704 Calcium Zinc Resinate	80 – 85	60 – 80 in MTO	100 – 110	1 : α to MTO	10 Max	Primers and Foundry industries
705 Calcium Magnesium Resinate	80 – 85	60 – 80 in MTO	100 – 110	1 : α to MTO	10 Max	Primers and Foundry industries