

TECHNICAL DATA SHEET

ZEOLEX 323

Aluminosilicate (Precipitated Amorphous Silicate)

■ Specifications:

• Form	White Powder
• Heating loss, 2hr/105°C, max as packaged	6.0
• pH, 20%	9.8 - 10.6
• Oil Absorption CC/100 gms	100 - 120
• Sieve Residue, #325 mesh (%max)	0.2
• Na ₂ SO ₄ , % max.	2.0

■ Standard Package:

- Multilayered paper bag, 20 kg net

Information obtained in these studies is based on materials and laboratory tests believed to be reliable; however, no guarantee is implied or expressed regarding the accuracy of these data or the use of the product. Esaar International does not represent that any of its products should be used in any manner which would infringe patent rights of others.