

TECHNICAL DATA SHEET

ZEOLEX 325

Magnesium Aluminium Silicate (Precipitated Amorphous Silicate)

■ Specifications:

• Form	White Powder
• Heat loss, 2hr/105°C, %max as packaged	7.0
• pH, 20% slurry	7.5 - 8.5
• APS (Microtrac), micron, max.	6.0
• Oil absorption, cc/100gm	95-125
• % Na ₂ SO ₄ , max.	2.0
• ISO, Brightness, min.	95.0

■ Standard Package:

- Multilayered paper bag, 25 Kgs net

Information obtained in these studies is based on materials and laboratory tests believed to be reliable; however, no guarantee is implied or expressed regarding the accuracy of these data or the use of the product. Esaar International does not represent that any of its products should be used in any manner which would infringe patent rights of others.