

# SAICRON ME Brand Reactive Dyes

Saicron ME Dyes	Shade 1.0%	Shade 3.0%	FASTNESS PROPERTIES			
			Light	Washing	Perspiration	Hypochlorite
<b>Gold. Yellow MERL</b> Reactive Yellow 145			5	5	4	4
<b>Yellow ME 4GL</b> Reactive Yellow 160			6	4-5	4-5	1
<b>Orange ME 2RL</b> Reactive Orange 122			5	5	4	2
<b>Red ME 4BL</b> Reactive Red 195			6	4-5	4-5	3
<b>Red GF</b> Reactive Red 223			5	4-5	4	2
<b>Red ME 6BL</b> Reactive Red 250			5	4-5	4	3-4
<b>Navy Blue ME 2GL</b> Reactive Blue 194			4-5	4-5	4	1
<b>Blue BRF</b> Reactive Blue 221			6-7	4	4	2
<b>Navy Blue BF</b> Reactive Blue 222			4-5	4	4	2
<b>Black HFGR</b> Reactive Black			4	5	4	3
<b>Black WNN</b> Reactive Black			5-6	4-5	4-5	2

The selection and shade chart are for illustration only, users / customers are requested to consider them only as guidelines. The given information is to the best of our knowledge, without obligation.